

Enkagrid[®] PRO 60

Enkagrid[®] PRO 60 is a rigid uniaxial geogrid composed of highly oriented extruded polyester strips. The polyester strips are bonded using laser technology that precisely controls the production process creating consistently rigid junctions. Enkagrid[®] PRO 60 is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value
			Machine Direction
Tensile Strength (at ultimate)	ASTM D 4595	kN/m (lbs/ft)	60 (4112)
Tensile Strength (at 2% strain)	ASTM D 4595	kN/m (lbs/ft)	14 (959)
Tensile Strength (at 5% strain)	ASTM D 4595	kN/m (lbs/ft)	30 (2056)
Creep Reduced Strength	ASTM D 5262	kN/m (lbs/ft)	41.4 (2837)
Long Term Allowable Design Load*	GRI GG-4	kN/m (lbs/ft)	33.0 (2262)

* NOTE: Long Term Allowable Design values are for sand, silt and clay.

Physical Properties	Test Method	Unit	Typical Value
Grid Aperture Size (MD x CD)	--	mm (in)	94 (3.7) x 42 (1.65)
Mass/Unit Area	ASTM D 5261	g/m ² (oz/yd ²)	218 (6.4)
Roll Dimensions (length x width)	--	m (ft)	5 (16.4) X 100 (328)
Roll Area	--	m ² (yd ²)	500 (598)
Estimated Roll Weight	---	kg (lbs)	135 (297)

DISCLAIMER: To the best of our knowledge, the information contained herein is accurate. However, Colbond Inc. cannot assume any liability whatsoever for the accuracy or completeness thereof. Final determination of the suitability of any information or material for the use contemplated, of its manner of use and whether the suggested use infringes any patents is the sole responsibility of the user.

© Colbond Geosynthetics