



## Product Information

# Colback® Fabrics

Spunlaid  
 Bi-component filaments (polyester core, nylon 6 skin)  
 Thermally bonded  
 Isotropic  
 Black

Type	TM100	TM120	TM135
------	-------	-------	-------

### Typical Properties

Mass per unit area	DIN 53854	g/m <sup>2</sup>	100	120	135
	DIN 53854	oz/yd <sup>2</sup>	2.95	3.54	3.98
Thickness	DIN 53855	mm	0.55	0.60	0.65
Breaking strength, MD	DIN 53857	N/5cm	310.7	368.5	417.7
		Lbs/in	34.9	41.4	46.9
Breaking strength, CMD	DIN 53857	N/5cm	282.9	311.4	396.2
		Lbs/in	31.8	35.0	44.5
Elongation to break, MD	DIN 53857	%	23.8	23.5	25.7
Elongation to break, CMD	DIN 53857	%	25.8	25.3	26.7
Dtex per filament		Dpf	10	10	10

### Roll Dimensions

Typical Length	m	915	915	800
	yd	1000	1000	875
Maximum Width	cm	530	530	530
	in	208	208	208
Typical Diameter	mm	838	863	863
	in	33	34	34
Cardboard Tube	mm	120	120	120
	in	4.72	4.72	4.72

The data are average values

11/00

Colbond Inc.

P.O. Box 1057  
 Enka, N.C. 28728  
 USA  
 Phone +1 (0)828 6655000  
 Fax +1 (0)828 6655005

We do not undertake any liability for the results of usage of these products. The technical data set forth in this datasheet reflect our best knowledge at the time of issue. The datasheet is subject to changes pursuant to new developments and findings, and a similar reservation applies to the properties of the products described.

A member of the **ACORDIS** group